

3:1 Heat shrink tube with glue.

Dual wall Tubing diameter: 1.62/2.4/3.2/4.8/6.4/7.9/9.5/12.7mm.

Specifications:

Double wall tube characteristics:

- 3:1 Shrinkage ratio, suitable for irregular shape insulation and sealing.
- Medium wall thickness, while maintaining flexibility, enhanced mechanical protection strength.
- The adhesive layer can be bonded to plastic, rubber and metal.
- The initial contraction temperature is 70 C, and the total shrinkage temperature is 125 C.
- The melting temperature of the inner layer: 70 C -100 C;
- The range of working temperature: -40 C ~ 125 C

Spe (mm)	Pre contraction inner diamether	Pre contraction wall thickness	After contraction(mm)		
			Internal diamether	Wall thickness	Adhesive layer thickness
2.4/0.8	≥2.4	0.4mm	0.8	1.0±0.15	0.35±0.1
3.2/1.0	≥3.2	0.4mm	1	1.0±0.15	0.35±0.1
4.8/1.6	≥4.8	0.5mm	1.6	1.1±0.15	0.4±0.1
6.4/2.2	≥6.4	0.5mm	2.2	1.25±0.15	0.45±0.1
7.9/2.7	≥7.9	0.6mm	2.7	1.3±0.15	0.5±0.1
9.2/3.2	≥9.5	0.6mm	3.2	1.4±0.15	0.5±0.1
12.7/4.2	≥12.7	0.7mm	4.2	1.7±0.15	0.55±0.1
15/5.2	≥15	0.8mm	5.2	1.8±0.15	0.55±0.1
19.1/6.3	≥19.1	0.8mm	6.3	2.0±0.15	0.55±0.1
25.4/8.5	≥25.4	0.9mm	8.5	2.1±0.15	0.55±0.1
30/10.2	≥30	1.0mm	10.2	2.2±0.15	0.6±0.1
40/13	≥40	1.0mm	13	2.5±0.15	0.6±0.1
50/17	≥50	1.1mm	17	2.8±0.15	0.8±0.1
60/20	≥60	1.1mm	20	3.0±0.15	0.9±0.1
70/23	≥70	1.2mm	23	3.2±0.15	1.0±0.1
80/26.5	≥80	1.2mm	26.5	3.5±0.15	1.0±0.1
90/30	≥90	1.2mm	30	3.5±0.15	1.1±0.1
100/34	≥100	1.2mm	34	3.5±0.15	1.2±0.1
120/40	≥120	1.2mm	40	3.5±0.15	1.2±0.1

EARU

